

Please insert the following passage beginning at page 15, line 12:

B2

-- Table 1 shows comparison in performances between a thin-walled circular-shaped metal structure fabricated by spinning working in accordance with the present invention and a thin-walled circular-shaped metal structure fabricated by drawing as a conventional method. It is assumed in Table 1 that a circular-shaped metal structure is used as a fixing roller.

[Table 1]

Thickness [mm]	Invention				Drawing			
	A	B	C	D	A	B	C	D
0.10	○	○	○	○	○	○	○	○
0.09	○	○	○	○	x	x	x	x
0.08	○	○	○	○	x	x	x	x
0.07	○	○	○	○	x	x	x	x
0.06	○	○	○	○	x	x	x	x
0.05	○	○	○	○	x	x	x	x
0.04	○	○	○	○	x	x	x	x
0.03	○	○	○	○	x	x	x	x
0.02	x	x	x	x	x	x	x	x

In Table 1, column "A" indicates uniformity in thickness, column "B" indicates straightness, column "C" indicates hardness, and column "D" indicates total estimate. A circle (○) in columns A, B and C indicates that the circular-shaped metal structure passes the test, and a cross (x) in columns A, B and C indicates the circular-shaped metal structure cannot pass the test.

For instance, a circular-shaped metal structure having a thickness of 0.09 mm, fabricated in accordance with the present invention, passes the tests with respect to uniformity in thickness, straightness and hardness, whereas a circular-shaped metal structure having a thickness of 0.09

HAYES SOLOWAY P.C.

130 W. CUSHING ST.
TUCSON, AZ 85701
TEL. 520.882.7623
FAX. 520.882.7643

175 CANAL STREET
MANCHESTER, NH 03101
TEL. 603.668.1400
FAX. 603.668.8567

mm, fabricated in accordance with the conventional method, cannot pass the tests with respect to the same.

BZ

In Table 1, both a circular-shaped metal structure fabricated in accordance with the present invention and a circular-shaped metal structure fabricated in accordance with a conventional method, that is, drawing are tested with respect to uniformity in thickness, straightness and hardness. A total estimate in column D was made taking the results of the tests in columns A, B and C into consideration. A circle (O) in column D indicates that the circular-shaped metal structure is practically usable, and a cross (x) in column D indicates the circular-shaped metal structure is practically unusable.

As is obvious in view of Table 1, a thin-walled circular-shaped metal structure fabricated in accordance with the conventional method has to have a thickness of 0.10 mm or greater in order to be practically usable. Even if a circular-shaped metal structure having a thickness of 0.09 mm or smaller is fabricated in accordance with the conventional method, the circular-shaped metal structure cannot be practically usable.

In contrast, as is obvious in view of Table 1, the present invention can provide a circular-shaped metal structure having a thickness in the range of 0.03 mm to 0.10 mm both inclusive, which is practically usable.

Thus, the present invention makes it possible to fabricate a circular-shaped metal structure having a thickness of 0.09 mm or smaller, which could not be fabricated in accordance with the conventional method.--

IN THE CLAIMS:

Kindly cancel claims 3, ~~6~~ and 21, without prejudice.

HAYES SOLOWAY P.C.

130 W. CUSHING ST.
TUCSON, AZ 85701
TEL. 520.882.7623
FAX. 520.882.7643

175 CANAL STREET
MANCHESTER, NH 03101
TEL. 603.668.1400
FAX. 603.668.8567